


Schlösser Möller Kulde A/S Postboks 65 Bryn 0611 Oslo Norway		Your order B116741			
		Our reference 132294	Packing slip / Date PS536295 7.8.2020		
		Your reference Lasse Djupvik			
Item	Product , Grade and Size				
004	Cupori 210 Ref kopparrör EN 12735-1 Cu-DHP R290 9,53 (3/8)X0,76 MM X 5 M Nitrogenfylda	740.12 Kg 3960.00 M		PU132294.4	
005	Cupori 210 Ref kopparrör EN 12735-1 Cu-DHP R290 12,7 (1/2)X0,89 MM X 5 M Nitrogenfylda	746.86 Kg 2530.00 M		PU132294.5	
006	Cupori 210 Ref kopparrör EN 12735-1 Cu-DHP R290 15,88 (5/8)X1,02 MM X 5 M Nitrogenfylda	374.62 Kg 880.00 M		PU132294.6	
007	Cupori 210 Ref kopparrör EN 12735-1 Cu-DHP R290 19,05 (3/4)X1,07 MM X 5 M Nitrogenfylda	370.11 Kg 685.00 M		PU132294.7	
According to: EN 12735-1					
Mechanical properties					
Item	Tensile strength R _m N/mm ²	0.2 % proof strength R _{p0.2} N/mm ²	Elongation %	Hardness	Grain size mm
004	473	446	A5 10		
005	477	451	A5 10		
006	456	423	A5 8		
007	457	415	A5 11		
Chemical composition % Cu-DHP/CW024A Cu min 99,90 P 0,03					
EDDY CURRENT TESTED:100%					
Electrical conductivity at 20 ° C % IACS (mass), annealed			We hereby certify, that the material described above complies with the order.  Teemu Pihl <small>This document has been printed out through electrical mail. A copy with original signature is available in our factory.</small>		
These products have been produced under a certified Quality System ISO 9001: 2015 / DNV Certificate No.80561-2010-AQ-FIN-FINAS					

Cupori Oy

P.O. Box 60, FIN-28101, Pori, Finland
 Tel. +358 2 511 4111, Fax +358 2 511 4002
 Domicile: Pori, Finland. Business ID 2639859-8, VAT FI26398598

Schlösser Möller Kulde A/S Postboks 65 Bryn 0611 Oslo Norway	Your order B116741	
	Our reference 132294	Packing slip / Date PS536295 7.8.2020
	Your reference Lasse Djupvik	

Item	Product , Grade and Size			
008	Cupori 210 Ref kopparrör EN 12735-1 Cu-DHP R290 22,23 (7/8)X1,14 X 5 M Nitrogenfylda	742.72	Kg	PU132294.8
		1100.00	M	
009	Cupori 210 Ref kopparrör EN 12735-1 Cu-DHP R290 28,58 (1 1/8)X 1,27 MM X 5 M Nitrogenfylda	375.03	Kg	PU132294.9
		385.00	M	
010	Cupori 210 Ref kopparrör EN 12735-1 Cu-DHP R290 34,93(1 3/8)X1,4 MM X 5 M Nitrogenfylda	375.63	Kg	PU132294.10
		285.00	M	
011	Cupori 210 Ref kopparrör EN 12735-1 Cu-DHP R290 53,98(2 1/8)X1,78 MM X 5 M Nitrogenfylda	365.40	Kg	PU132294.11
		140.00	M	

According to: EN 12735-1

Mechanical properties

Item	Tensile strength R _m N/mm ²	0.2 % proof strength R _{p0.2} N/mm ²	Elongation %	Hardness	Grain size mm
008	461	430	A5	8	
009	459	428	A5	8	
010	450	445	A5	5	
011	365	340	A5	10	

Chemical composition %

Cu-DHP/CW024A
 Cu min 99,90
 P 0,03

EDDY CURRENT TESTED:100%

Electrical conductivity at 20 ° C % IACS (mass), annealed

We hereby certify, that the material described above complies with the order.

These products have been produced under a certified Quality System
 ISO 9001: 2015 / DNV Certificate No.80561-2010-AQ-FIN-FINAS



Teemu Pihl

This document has been printed out through electrical mail.
 A copy with original signature is available in our factory.

Cupori Oy

P.O. Box 60, FIN-28101, Pori, Finland
 Tel. +358 2 511 4111, Fax +358 2 511 4002
 Domicile: Pori, Finland. Business ID 2639859-8, VAT FI26398598