

Schlösser Möller Kulde A/S Postboks 65 Bryn 0611 Oslo Norway	Your order B117531	
	Our reference 132993	Packing slip / Date PS537096 16.10.2020
	Your reference Lasse Djuvik	

Item	Product, Grade and Size			
007	Cupori 210 Ref kopparrör EN 12735-1 Cu-DHP R290 34,93(1 3/8)X1,4 MM X 5 M Nitrogenfylda	395.40	Kg	PU132993.7
		300.00	M	
008	Cupori 210 Ref kopparrör EN 12735-1 Cu-DHP R290 53,98(2 1/8)X1,78 MM X 5 M Nitrogenfylda	391.50	Kg	PU132993.8
		150.00	M	

According to: EN 12735-1

Mechanical properties

Item	Tensile strength R _m N/mm ²	0.2 % proof strength R _{p0.2} N/mm ²	Elongation %	Hardness	Grain size mm
007	445	441	A5	4	
008	384	380	A5	7	

Chemical composition %

Cu-DHP/CW024A
 Cu min 99,90
 P 0,03

EDDY CURRENT TESTED:100%

Electrical conductivity at 20 ° C % IACS (mass), annealed

We hereby certify, that the material described above complies with the order.

These products have been produced under a certified Quality System
 ISO 9001: 2015 / DNV Certificate No.80561-2010-AQ-FIN-FINAS



Teemu Pihl
 This document has been printed out through electrical mail.
 A copy with original signature is available in our factory.

Cupori Oy

P.O. Box 60, FIN-28101, Pori, Finland
 Tel. +358 2 511 4111, Fax +358 2 511 4002
 Domicile: Pori, Finland. Business ID 2639859-8, VAT FI26398598