

Schlösser Möller Kulde A/S Postboks 65 Bryn 0611 Oslo Norway	Your order B117219	
	Our reference 132733	Packing slip / Date PS536860 25.9.2020
	Your reference Lasse Djupvik	

Item	Product , Grade and Size			
001	Cupori 210 Ref kopparrör EN 12735-1 Cu-DHP R290 9,53 (3/8)X0,76 MM X 5 M Nitrogenfylda	766.29	Kg	PU132733.1
		4100.00	M	
002	Cupori 210 Ref kopparrör EN 12735-1 Cu-DHP R290 12,7 (1/2)X0,89 MM X 5 M Nitrogenfylda	1084.86	Kg	PU132733.2
		3675.00	M	
006	Cupori 210 Ref kopparrör EN 12735-1 Cu-DHP R290 28,58 (1 1/8)X 1,27 MM X 5 M Nitrogenfylda	599.07	Kg	PU132733.6
		615.00	M	

According to: EN 12735-1

Mechanical properties

Item	Tensile strength R _m N/mm ²	0.2 % proof strength R _{p0.2} N/mm ²	Elongation %	Hardness	Grain size mm
001	473	442	A5	6	
002	479	456	A5	7	
006	452	417	A5	6	

Chemical composition %

Cu-DHP/CW024A
 Cu min 99,90
 P 0,03

EDDY CURRENT TESTED:100%

Electrical conductivity at 20 ° C % IACS (mass), annealed

We hereby certify, that the material described above complies with the order.

These products have been produced under a certified Quality System
 ISO 9001: 2015 / DNV Certificate No.80561-2010-AQ-FIN-FINAS



Teemu Pihl

This document has been printed out through electrical mail.
 A copy with original signature is available in our factory.

Cupori Oy

P.O. Box 60, FIN-28101, Pori, Finland
 Tel. +358 2 511 4111, Fax +358 2 511 4002
 Domicile: Pori, Finland. Business ID 2639859-8, VAT FI26398598